



1 Floor, No.14 building, Small and Medium sized Enterprises Pioneer Park, SSL Industry Park, Dongguan - P.R. CHINA Tél.: +86 769 23 03 77 70

Fax: +86 769 23 03 77 71 E-mail: ctcdongguan@ctcgroupe.com





### **TEST REPORT**

Page 1/4

Report No.: D220815465\_1

10 August 2022

检验检测专用

APPLICANT: RUIAN SHENGFA SHOES MATERIAL CO., LTD

(C40228)

瑞安市上望街道闻涛路88号置慧工业

园13幢(102-502) . WENZHOU ZHEJIANG

CHINA

:01 Aug. 2022 Date of receipt

Testing period :01 Aug. 2022

:10 Aug. 2022

Buyer: --

Style / Article no. :459

Test(s) requested : PHYSICAL TEST

Service : REGULAR Brand / Section Season

End use

Factory name Factory code

Previous report

Product category Product type

:FIRST TEST Test stage

Supplier name Exported to

#### 1. Conclusion:

| ISO 22568-2 : 2019 |                            | Conformity by size |      |      |  |
|--------------------|----------------------------|--------------------|------|------|--|
| Paragraph#         | <u>Tests description</u>   | 06                 | 08   | 11   |  |
| 4.4                | Impact resistance          | Pass               | Pass | Pass |  |
| 4.5                | Compression resistance     | Pass               | Pass | Pass |  |
| 4.6                | Effect of fuel oil         | -                  | Pass | -    |  |
| 4.6                | Effect of high temperature | -                  | Pass | -    |  |
| 4.6                | Effect of low temperature  |                    | Pass |      |  |

Pass: requirements met Fail: requirements not met N/A: not applicable --: test not performed on this size

Approved by

Leo TOM KIT FAI Operational Manager









# **TEST REPORT**

Page 2/4

Report No.: D220815465\_1

10 August 2022

APPLICANT: RUIAN SHENGFA SHOES MATERIAL CO., LTD

(C40228)

#### 2. Sample(s) description assigned by laboratory:

| Size | Analyzed product | <u>Description</u> | Sample information |
|------|------------------|--------------------|--------------------|
| 06   | Toecap (2 pairs) |                    |                    |
|      |                  | Accessory          | Toecap             |
| Size | Analyzed product | <u>Description</u> | Sample information |
| 08   | Toecap (5 pairs) |                    |                    |
|      |                  | Accessory          | Toecap             |
| Size | Analyzed product | <u>Description</u> | Sample information |
| 11   | Toecap (2 pairs) |                    |                    |
|      |                  | Accessory          | Тоесар             |



D220815465







中国认可 国际互认 检测 TESTING CNAS L5912

# **TEST REPORT**

Page 3/4

检验检测专用章

Report No.: D220815465\_1

10 August 2022

APPLICANT: RUIAN SHENGFA SHOES MATERIAL CO., LTD

| Toecap / Accessory : Toecap Method Requireme |                  |       | ent   |       | Result |         |         |         | _          |   |   |
|--|------------------|-------|-------|-------|--------|---------|---------|---------|------------|---|---|
| Toecap / Accessory : Toecap                  | Method           | Size  |       |       | Unit   | Size    |         |         | Conformity |   |   |
|  |                  | 06    | 08    | 11    |        | 06      | 08      | 11      |            |   |   |
| (+) 4.4. Impact resistance                   | ISO 22568-2:2019 |       |       |       |        |         |         |         | Р          | Р | Р |
| Toecap type                                  |                  |       |       |       |        | Α       | Α       | А       |            |   |   |
| Clearance - left foot                        |                  | ≥20.0 | ≥21.0 | ≥22.0 | mm     | 26.0    | 25.0    | 26.0    |            |   |   |
| Clearance - right foot                       |                  | ≥20.0 | ≥21.0 | ≥22.0 | mm     | 25.5    | 25.5    | 26.0    |            |   |   |
| Development of cracks or delamination        |                  | '     |       | 1     |        | Conform | Conform | Conform |            |   |   |
| Development of sharp edges                   |                  |       |       |       |        | Conform | Conform | Conform |            |   |   |
| (+) 4.5. Compression                         | ISO 22568-2:2019 |       |       |       |        |         |         |         | Р          | Р | Р |
| resistance                                   |                  |       |       |       |        |         |         |         |            |   |   |
| Toecap type                                  |                  |       |       |       |        | A       | A       | A       |            |   |   |
| Clearance - left foot                        |                  | ≥20.0 | ≥21.0 | ≥22.0 | mm     | >30     | >30     | >30     |            |   |   |
| Clearance - right foot                       |                  | ≥20.0 | ≥21.0 | ≥22.0 | mm     | >30     | >30     | >30     |            |   |   |
| Development of cracks or delamination        |                  |       |       |       |        | Conform | Conform | Conform |            |   |   |
| Development of sharp edges                   |                  |       |       |       |        | Conform | Conform | Conform |            |   |   |
| (+) 4.6. Effect of high                      | ISO 22568-2:2019 |       |       |       |        |         |         |         |            | Р |   |
| temperature<br>Toecap type                   |                  |       |       |       |        |         | A       |         |            |   |   |
| Clearance - left foot                        |                  |       | ≥21.0 |       | mm     |         | 24.5    |         |            |   |   |
| Clearance - right foot                       |                  |       | ≥21.0 |       | mm     |         | 25.0    |         |            |   |   |
| Development of cracks or delamination        |                  |       |       |       |        |         | Conform |         |            |   |   |
| Development of sharp edges                   |                  |       |       |       |        |         | Conform |         |            |   |   |
| (+) 4.6. Effect of fuel oil                  | ISO 22568-2:2019 |       |       |       |        |         |         |         |            | Р |   |
| Toecap type                                  |                  |       |       |       |        |         | A       |         |            |   |   |
| Clearance - left foot                        |                  |       | ≥21.0 |       | mm     |         | 26.0    |         |            |   |   |
| Clearance - right foot                       |                  |       | ≥21.0 |       | mm     |         | 25.0    |         |            |   |   |
| Development of cracks or delamination        |                  |       |       |       |        |         | Conform |         |            |   |   |
| Development of sharp edges                   |                  |       |       |       |        |         | Conform |         |            |   |   |
| (+) 4.6. Effect of low                       | ISO 22568-2:2019 |       |       |       |        |         |         |         |            | Р |   |
| temperature                                  |                  |       |       |       |        |         |         |         |            |   |   |
| Toecap type                                  |                  |       |       |       |        |         | Α       |         |            |   |   |
| Clearance - left foot                        |                  |       | ≥21.0 |       | mm     |         | 26.0    |         |            |   |   |
| Clearance - right foot                       |                  |       | ≥21.0 |       | mm     |         | 26.5    |         |            |   |   |
| Development of cracks or delamination        |                  |       |       |       |        |         | Conform |         |            |   |   |
| Development of sharp edges                   |                  |       |       |       |        |         | Conform |         |            |   |   |

The report is issued by CTC Dongguan under its General Conditions printed overleaf. The results shown in this report refer only to the sample (s) tested. Except by special arrangement, the test items will not be retained by CTC Dongguan for more than 3 months. The test report shall not be retained by CTC Dongguan for more than 3 months. The test report shall not be retained by CTC Dongguan for more than 3 months. in full, without the written approval of the testing laboratory.









### **TEST REPORT**

Page 4/4

Report No.: D220815465\_1

10 August 2022

APPLICANT: RUIAN SHENGFA SHOES MATERIAL CO., LTD

(C40228)

#### **END OF TEST REPORT**

(+)CNAS accreditation