

# TEST REPORT

Page 1/4

Report No.: D220815467\_1

10 August 2022

**APPLICANT:** RUIAN SHENGFA SHOES MATERIAL CO., LTD  
(C40228)  
瑞安市上望街道闻涛路88号置慧工业  
园13幢(102-502)  
. WENZHOU ZHEJIANG  
CHINA

Date of receipt : 29 July 2022  
Testing period : 29 July 2022  
: 10 Aug. 2022

**Buyer:** —

Style / Article no. : 522  
Test(s) requested : PHYSICAL TEST  
Service : REGULAR  
Brand / Section : —  
Season : —  
End use : —  
Factory name : —  
Factory code : —

Previous report : —  
Product category : —  
Product type : —  
Test stage : FIRST TEST  
Supplier name : —  
Exported to : —

## 1. Conclusion:

ISO 22568-2 : 2019		Conformity by size		
Paragraph#	Tests description	06	08	11
4.4	Impact resistance	Pass	Pass	Pass
4.5	Compression resistance	Pass	Pass	Pass
4.6	Effect of fuel oil	--	Pass	--
4.6	Effect of high temperature	--	Pass	--
4.6	Effect of low temperature	--	Pass	--

Pass: requirements met    Fail: requirements not met    N/A: not applicable    --: test not performed on this size

Approved by



Leo TOM KIT FAI  
Operational Manager

# TEST REPORT

Page 2/4

Report No.: D220815467\_1

10 August 2022

APPLICANT: RUIAN SHENGFA SHOES MATERIAL CO., LTD  
(C40228)

## 2. Sample(s) description assigned by laboratory:

<u>Size</u>	<u>Analyzed product</u>	<u>Description</u>	<u>Sample information</u>
06	Toecap (2 pairs)	Accessory	Toecap
<u>Size</u>	<u>Analyzed product</u>	<u>Description</u>	<u>Sample information</u>
08	Toecap (5 pairs)	Accessory	Toecap
<u>Size</u>	<u>Analyzed product</u>	<u>Description</u>	<u>Sample information</u>
11	Toecap (2 pairs)	Accessory	Toecap



D220815467

The report is issued by CTC Dongguan under its General Conditions printed overleaf. The results shown in this report refer only to the sample(s) tested. Except by special arrangement, the test items will not be retained by CTC Dongguan for more than 3 months. The test report shall not be reproduced, except in full, without the written approval of the testing laboratory.

To declare the conformity to the requirement, the uncertainty of measurement, associated to the test results, has not been taken into account.



# TEST REPORT

Page 3/4

Report No.: D220815467\_1

10 August 2022

APPLICANT: RUIAN SHENGFA SHOES MATERIAL CO., LTD  
(C40228)

Toecap / Accessory : Toecap	Method	Requirement Size			Unit	Result Size			Conformity
		06	08	11		06	08	11	
(+) <b>4.4. Impact resistance</b>	ISO 22568-2:2019								P P P
Toecap type						A	A	A	
Clearance - left foot		≥20.0	≥21.0	≥22.0	mm	26.0	27.0	28.0	
Clearance - right foot		≥20.0	≥21.0	≥22.0	mm	25.5	27.0	28.0	
Development of cracks or delamination						Conform	Conform	Conform	
Development of sharp edges						Conform	Conform	Conform	
(+) <b>4.5. Compression resistance</b>	ISO 22568-2:2019								P P P
Toecap type						A	A	A	
Clearance - left foot		≥20.0	≥21.0	≥22.0	mm	>30	>30	>30	
Clearance - right foot		≥20.0	≥21.0	≥22.0	mm	>30	>30	>30	
Development of cracks or delamination						Conform	Conform	Conform	
Development of sharp edges						Conform	Conform	Conform	
(+) <b>4.6. Effect of high temperature</b>	ISO 22568-2:2019								-- P --
Toecap type						--	A	--	
Clearance - left foot			≥21.0		mm	--	26.0	--	
Clearance - right foot			≥21.0		mm	--	26.0	--	
Development of cracks or delamination						--	Conform	--	
Development of sharp edges						--	Conform	--	
(+) <b>4.6. Effect of fuel oil</b>	ISO 22568-2:2019								-- P --
Toecap type						--	A	--	
Clearance - left foot			≥21.0		mm	--	26.5	--	
Clearance - right foot			≥21.0		mm	--	27.0	--	
Development of cracks or delamination						--	Conform	--	
Development of sharp edges						--	Conform	--	
(+) <b>4.6. Effect of low temperature</b>	ISO 22568-2:2019								-- P --
Toecap type						--	A	--	
Clearance - left foot			≥21.0		mm	--	27.0	--	
Clearance - right foot			≥21.0		mm	--	27.0	--	
Development of cracks or delamination						--	Conform	--	
Development of sharp edges						--	Conform	--	

The report is issued by CTC Dongguan under its General Conditions printed overleaf. The results shown in this report refer only to the sample(s) tested. Except by special arrangement, the test items will not be retained by CTC Dongguan for more than 3 months. The test report shall not be reproduced, except in full, without the written approval of the testing laboratory.

To declare the conformity to the requirement, the uncertainty of measurement, associated to the test results, has not been taken into account.



## TEST REPORT

Page 4/4

Report No.: D220815467\_1

10 August 2022

APPLICANT: RUIAN SHENGFA SHOES MATERIAL CO., LTD  
(C40228)

---

### END OF TEST REPORT

(+)CNAS accreditation

The report is issued by CTC Dongguan under its General Conditions printed overleaf. The results shown in this report refer only to the sample(s) tested. Except by special arrangement, the test items will not be retained by CTC Dongguan for more than 3 months. The test report shall not be reproduced, except in full, without the written approval of the testing laboratory.

To declare the conformity to the requirement, the uncertainty of measurement, associated to the test results, has not been taken into account.

